



## ZEFFLE Products

### Fluororesins for coatings, paints, inks, adhesives, surface protection, films

| Product Name | % wt Solids | OH Value (mg KOH/g resin) | Solvent                         | Registration | Description                                                                                   | Typical Markets                                                                   | Other Comments                                        |
|--------------|-------------|---------------------------|---------------------------------|--------------|-----------------------------------------------------------------------------------------------|-----------------------------------------------------------------------------------|-------------------------------------------------------|
| GK-870       | 65%         | 61-65                     | n-butyl acetate                 | TSCA         | Standard crosslinkable FEVE resin for weatherability, chemical, solvent, and stain resistance | Protective coatings, renewable energy, oil and gas, protective films, electronics | Crosslinkable with polyisocyanates and melamine, etc. |
| S-7542A      | 75%         | 55-65                     | t-butyl acetate/n-butyl acetate | TSCA         | Low VOC FEVE resin for paints                                                                 | Heavy industrial, aerospace, architectural, bridge, and roofing paints            |                                                       |
| GK-571       | 50%         | 55-65                     | n-butyl acetate/Solvesso 100    | TSCA         | Coil coating grade of FEVE with slow solvent for improved processability                      | Architectural, aluminum and steel extrusion                                       |                                                       |
| S-7510       | 51%         | N/A                       | Water                           | TSCA         | Waterborne 1K resin MFFT 40-46°C                                                              | Architectural, wood, masonry, metal, vinyl paints                                 | Particle Size ~160 nm                                 |
| S-7520       | 51%         | N/A                       | Water                           | TSCA         | Waterborne 1K resin MFFT 6-14°C                                                               | Architectural, wood, masonry, metal, vinyl paints                                 | Particle Size ~180 nm                                 |
| SE-2K        | 50%         | 10                        | Water                           | Pending TSCA | Developmental waterborne 2K resin                                                             | Waterborne or Low VOC high performance applications                               | Developmental                                         |

### Hydrophilic additive for self cleaning exterior coatings

| Product Name | % wt Solids | Usage Level                                      | Compatible with           | Description                            | Typical Markets                                              | Other Comments                                      |
|--------------|-------------|--------------------------------------------------|---------------------------|----------------------------------------|--------------------------------------------------------------|-----------------------------------------------------|
| GH-701       | 100%        | 1-5% wt on solids (Clear)<br>2-3% wt (Pigmented) | Solventborne 2K Urethanes | Hydrophilic additive for self cleaning | Exterior UV durable applications with aesthetic requirements | Creates a 'self cleaning' effect with rain exposure |